

• TRUSTED QUALITY SINCE 1921 •

RUST-OLEUM®
SPECIALTY

**SPECIALTY
FARM EQUIPMENT SPRAYS**

DESCRIPTION AND USES

Farm Equipment is a durable, rust preventive enamel that is available in bright original equipment colors. This Stops Rust® formula offers excellent coverage, chip resistance and color retention. Farm Equipment Sprays are ideal for tractors, farm implements, lawn mowers, and more. Not for use on galvanized metal.

PRODUCTS

SKU	Description
7424830	Blue (Ford)
7435830	Green (John Deere)
7443830	Yellow (John Deere)
7449830	Yellow (Caterpillar)
7458830	Orange (Allis Chalmers)
7462830	Red (Massey Ferguson)
7466830	Red (International Harvester)

PRODUCT APPLICATION

SURFACE PREPARATION

ALL SURFACES: Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with a commercial detergent, or other suitable cleaning method. Mold and mildew must be cleaned with a chlorinated cleaner or bleach solution. Rinse with fresh water and allow to thoroughly dry.

STEEL: Scrape and wire brush or power tool clean to remove loose rust, scale and deteriorated coatings. Use 7769 Rusty Metal Primer for sound rusted or clean metal before application of a finish coat. 7780 Clean Metal Primer is best for clean metal but may be used on sound rusted metal as well.

PREVIOUSLY COATED: Previously coated surfaces must be sound and in good condition. Smooth, hard, or glossy finishes should be scarified by sanding to create a surface profile.

WARNING! LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you sand, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PRODUCT APPLICATION (cont.)

APPLICATION

Apply only when air and surface temperatures are between 50-90°F (10-32°C) and the relative humidity is below 85% to ensure proper drying. Protect the surrounding area from overspray. Overspray can carry a significant distance. Shake can vigorously for one minute after the mixing ball begins to rattle. If mixing ball fails to rattle **DO NOT STRIKE CAN**. Contact Rust-Oleum. Hold can upright 10-16" from surface and spray in a steady back and forth motion, slightly overlapping each stroke. Keep the can the same distance from the surface. Keep the can in motion while spraying. Apply two or more light coats a few minutes apart to avoid drips and runs. **Do not use near open flame.**

DRY & RECOAT

Dry and recoat times are based on 70°F (21°C) and 50% relative humidity. Dries to the touch in 2-4 hours and can be handled in 5-9 hours. Recoat within 1 hour or after 24 hours.

CLEAN-UP

Clean valve immediately after use by turning can upside down and depressing spray button for 3-5 seconds (some paint will be sprayed out, so be careful to not inadvertently spray yourself or other objects). Clean up wet paint with xylene or mineral spirits. Throw away empty can in trash pick-up. Do not burn or place in home trash compactor.

CLOGGING

If the valve clogs, twist and pull off spray tip and rinse in a solvent such as mineral spirits. Do not insert any object into can valve opening.

TECHNICAL DATA

FARM EQUIPMENT SPRAYS

PHYSICAL PROPERTIES

Physical Properties		FARM EQUIPMENT SPRAYS
Resin Type		Oil Modified Alkyd
Pigment Type		Varies with color
Solvents		Acetone, Ethyl Benzene, N-Butyl Acetate, Xylene
MIR		0.95 Max
Fill Weight		12 ounces
Practical Coverage at Recommended DFT (assumes 15% material loss)		Approximately 6-7 sq.ft./can (0.54-0.63 m ² /can)
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	2-4 hours
	Handle	5-9 hours
	Recoat	Within 1 hour or after 24 hours
Dry Heat Resistance		200°F (93°C)
Shelf Life		5 years
Flash Point		-156°F (-104°C)
Safety Information		For additional information, see SDS

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.